



### Vlastnosti

|                    |  |
|--------------------|--|
| Složení:           | ESD-PET//AL//ONY//ESD-PE                                   |
| Tloušťka:          | 155 μm/6,1 mil +/-10%                                      |
| Pevnost v tahu:    | MD: 10500 psi ASTM D882-91<br>TD: 9200 psi ASTM D882-91    |
| Pevnost v trhu:    | MD: 37,02 lbs ASTM D1004-66<br>TD: 39,87 lbs ASTM D1004-66 |
| Pružnost:          | MD: 125% ASTM D882-91<br>TD: 109% ASTM D882-91             |
| Svět. propustnost: | < 0,001% ASTM D-1003-92                                    |
| Síla sváru:        | > 157,84 lbs/in.width<br>FTMS D 1876-93                    |
| Roztržení:         | >145,04 psi FTMS 191-C                                     |
| Protržení:         | > 197,66 lbs FTMS 101-C                                    |
| MVTR @100F         | < 0,0006 g/100in <sup>2</sup> /24h                         |

IPC/JEDEC J-STD-033B.1



4-vrstvé složení

MIL-B 81705-REV-C



Tloušťka 155 μ

MVTR < 0,0006 g/100in<sup>2</sup>/24h

### Elek. vlastnosti

|                   |   |
|-------------------|---|
| EMI stínění:      | 30 dB MIL-B 81705-REV-C   |
| Statická ochrana: | < 15 Volts EIA-Std541   |
| Povrchový odpor:  | Interior < 10 Ohms/in <sup>2</sup><br>Exterior < 10 Ohms/in <sup>2</sup><br>Metal 100hms/in <sup>2</sup><br>ASTM D257 @15% RH |

| Produkt                          | Obj. číslo |
|----------------------------------|------------|
| Super Dry Bags 1066 100 x 660 mm | 90010066   |
| Super Dry Bags 1570 150 x 700 mm | 90015070   |
| Super Dry Bags 2550 250 x 500 mm | 90025050   |
| Super Dry Bags 2575 250 x 750 mm | 90025075   |
| Super Dry Bags 4244 420 x 440 mm | 90042550   |
| Super Dry Bags 4254 420 x 540 mm | 90042554   |